

COLONIAL BURNISHING COMPOUND

<u>Component</u>	<u>Wt. %</u>
Water	73.0
Sodium Nitrite	2.0
Urea	1.0
Cola [®] Mine CDA	1.5
Cola [®] Teric 2CM	4.5
Cola [®] Lube 3412 CI	17.5
Versene Acid	<u>0.5</u>
Total	100.0

PROCEDURE:

Blend and agitate as indicated.

This formulation provides superior lubricity and corrosion protection while providing excellent finishing properties.

Formula 168

Last Modified 07/25/2006

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.