



Heavy Duty Industrial Spray Metal Cleaner Concentrates

FORMULA 1

| <u>Compound</u> | <u>Wt %</u> |
|---------------------------------|---------------|
| Water | 65.0 |
| Potassium Hydroxide | 10.0 |
| Sodium Metasilicate (Anhydrous) | 10.0 |
| Sodium Carbonate | 5.0 |
| Colonial ZF-25 | 10.0 |
| TOTAL | 100.00 |

PROCEDURE: Mix ingredients in order listed with agitation.

TYPICAL PROPERTIES: Cloud Point 43°C
Krafft Point < 0°C

RECOMMENDED USE DILUTION: 6 to 8 oz./gal.

FORMULA 2

| <u>Compound</u> | <u>Wt %</u> |
|------------------------|---------------|
| Water | 40.0 |
| Sodium Hydroxide (50%) | 50.0 |
| Colonial ZF-25 | 10.0 |
| TOTAL | 100.00 |

PROCEDURE: Add ingredients in order listed with agitation.

TYPICAL PROPERTIES: Cloud Point 75°C
Krafft Point < 5°C

RECOMMENDED USE DILUTION: 1 to 4 oz./gal.

LAST UPDATED 07/20/2006

FORMULA NUMBER: 099

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.

Colonial Chemical, Inc.
www.colonialchem.com



ColonialChemical, Inc.