Low Temperature Aluminum Wash

DESCRIPTION:

Colonial ZF-10 provides excellent detergency and controlled foam while contributing to the protection of aluminum.

Compound	Wt %
Water	88.00
Sodium Metasilicate (Anhydrous)	2.00
Tetrasodium Pyrophosphate (Powder)	3.00
Butyl Carbitol*	2.00
Colonial ZF-10	5.00
TOTAL	**100.00**

PROCEDURE:

Dissolve sodium metasilicate and tetrapotassium pyrophosphate in water, then add Butyl Carbitol* and Colonial ZF-10.

PROPERTIES:

Appearance	Clear Liquid
pH	12.8
Recommended use dilution	Aluminum safe at 1:10 with water

*Union Carbide

LAST UPDATED 07/20/2006 FORMULA NUMBER: 013

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.

Colonial Chemical, Inc.

www.colonialchem.com

ColonialChemical, Inc.

225 Colonial Drive South Pittsburg, TN 37380 Ph: 423-837-8800 Fax: 423-837-3888