

# SEMI-SYNTHETIC FOR HEAVY DUTY MACHINING FLUID

---

<u>COMPOUND</u>	<u>% WT.</u>
100 SUS Napthenic Oil	20.0
Cola <sup>®</sup> Lube 3418EPL	26.0
Cola <sup>®</sup> Lube 3420EPL	26.0
Elco 217	5.0
Synalox EPB 660	5.0
Water	<u>18.0</u>
Total	100.0

Use at 5% in water.

Formula 155

Last Modified 07/27/2006

## WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.