

SYNTHETIC FOR GRINDING FOR FERROUS & NON-FERROUS METALS - 2

<u>COMPOUND</u>	<u>% WT.</u>
Cola [®] Lube 3406CI	12.5
Cola [®] Lube 3414EPL	12.5
TEA	25.0
Water	<u>50.0</u>
Total	100.0

PROCEDURE:

Mix ingredients in order listed until clear.

PERFORMANCE (5% in water):

Appearance	Clear liquid
pH	8.0
Cast Iron Block Test	Pass
Falex [®]	2250lbs / 45in-lbs

Formula 070

Last Modified 07/27/2006

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.