

# SYNTHETIC FOR GRINDING FERROUS METALS

---

<u>COMPOUND</u>	<u>% WT.</u>
Cola <sup>®</sup> Lube 3406CI	16.6
MEA	33.3
Water	<u>50.1</u>
Total	100.0

## **PROCEDURE:**

Mix ingredients in order listed until clear.

## **PERFORMANCE (5% in water):**

Appearance	Clear liquid
pH	11
Cast Iron Block Test	Pass
Falex <sup>®</sup>	2250lbs / 58in-lbs

Formula 061

Last Modified 07/27/2006

### **WARRANTY**

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.