



Vinyl, Leather, Rubber & Plastic Creamy Protectant

<u>Compound</u>	<u>Wt%</u>
Cola [®] Cor 600	2.0
Dow Corning 531 Fluid	2.0
LPA 140	23.0
Water	63.5
Dow Corning 929 Emulsion	8.0
Bentone 38	1.0
Anhydrous IPA	<u>0.5</u>
TOTAL	100.00

PROCEDURE:

Add Cola[®]Cor 600, 531 Fluid and LPA to a vessel and begin slow mixing. When uniform, slowly add water to the mixture. When thoroughly mixed, add 929 Emulsion. Sift or screen Bentone 38 into the mixture and mix until homogeneous. Add IPA and mix until creamy stable emulsion is formed. Isopar L may be substituted for LPA for lower odor formulation. Shake well before using.

LAST UPDATED 07/21/2006

FORMULA NUMBER: 147

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.

Colonial Chemical, Inc.

www.colonialchem.com



ColonialChemical, Inc.