

# WATER-BASED RUST INHIBITORS

---

## Suggested for Grinding Application

	<u>Compound</u>	<u>% Wt.</u>
A.	Water	70.0
	Cola <sup>®</sup> Cor RP	<u>30.0</u>
B.	Part A	5.0
	Water	<u>95.0</u>
	Total	100.0

## Suggested for Light Machining

	<u>Compound</u>	<u>% Wt.</u>
A.	Water	90.0
	Cola <sup>®</sup> Cor 400	<u>10.0</u>
B.	Part A	4.0
	Water	<u>96.0</u>
	Total	100.0

**Cast Iron Chip Test:** Pass-No rust  
**Foam:** None  
**pH:** 9.4

Pass-No rust  
Trace  
8.4

Last Modified 07/26/2006

Formula 169

### WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.