

# AEROSOL TIRE INFLATOR

---

<u>COMPOUND</u>	<u>% WT.</u>
Hycar 1578X1	7.50
Propylene Glycol	6.00
COLA™ COR AER	1.20
Ammonium Hydroxide	0.30
Fibracell SW10	0.45
DI Water	66.55
DME	6.00
HFC-134a	<u>12.00</u>
TOTAL	100.00

Formula 036

Last Modified 06/22/2005

## WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.