

# EXTRA HOLD CONDITIONING MOUSSE

---

	<u>COMPOUND</u>	<u>%</u>
I.	Water	37.35
	Amphomer	3.75
	Aminomethyl Propanol	0.60
	Dow Corning 929 Emulsion	0.40
	COLA™ LIPID SAFL	0.60
	SD3A Alcohol	10.00
II.	Hydroxyethyl Cellulose	0.30
	Water	37.00
III.	Propellant	10.00
	Total	<u>100.00</u>

## PROCEDURE:

Prepare Part I and II separately. To prepare Part II, carefully sprinkle hydroxyethyl cellulose into water with good agitation. Heat may be applied to help solubilization. Blend Part II to I and then aerosolize.

Last Modified 06/14/2005

Formula 107

### WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.