

LOW TEMPERATURE ALUMINUM WASH

DESCRIPTION:

COLONIAL ZF-10 provides excellent detergency and controlled foam while contributing to the protection of aluminum.

<u>COMPOUND</u>	<u>WT%</u>
Water	88.00
Sodium Metasilicate (Anhydrous)	2.00
Tetrasodium Pyrophosphate (Powder)	3.00
Butyl Carbitol*	2.00
COLONIAL ZF-10	5.00
Total	100.00

PROCEDURE:

Dissolve sodium metasilicate and tetrapotassium pyrophosphate in water, then add Butyl Carbitol* and Colonial ZF-10.

PROPERTIES:

Appearance	Clear Liquid
pH	12.8
Recommended use dilution	Aluminum safe at 1:10 with water

*Union Carbide

Formula 013

Last Modified 07/5/2005

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.