

OUTSIDE STORAGE CORROSION PREVENTATIVE

<u>COMPOUND</u>	<u>%</u>
COLA™COR THE	7.0
Bright Stock (150 SUS/210)	93.0
Total	<u>100.0</u>

PROCEDURE:

Warm oil to 110°F and add COLA™COR THE. Mix for 30 minutes. Apply to steel at 140°F.

Formula 136

Last Modified 07/9/2005

WARRANTY

Colonial Chemical guarantees that its products meet published specifications. No other warranties or guarantees are expressed or implied because the use of this material is beyond the control of Colonial Chemical.